

GP-215 SILICONE POLYOL COPOLYMER

Genesee Polymers' *GP-215 SILICONE POLYOL COPOLYMER* is a 100% active non-ionic silicone polyol surfactant.

GP-215 contains polyoxyethylene-polyoxypropylene copolymer blocks and dimethyl silicone polymer blocks, which are joined through non-hydrolyzable silicon to carbon bonds.

GP-215 SILICONE POLYOL COPOLYMER is designed to function as an emulsifier, wetting agent and profoaming additive for a variety of applications including polyurethane foams, hard surface cleaners and polishes and cosmetic formulations. GP-215 exhibits inverse solubility versus temperature characteristics, becoming insoluble in water as temperature is increased to approximately 40° C (104° F). This property suggests use as a defoamer for hot aqueous surfactant solutions.

GP-215 SILICONE POLYOL COPOLYMER contains no functional groups and is chemically inert, and essentially nontoxic.

TYPICAL PROPERTIES

Appearance Clear to Hazy, Colorless to Straw Liquid

Weight/Gallon 8.5 lbs

Viscosity 77° F 800 cSt

Flash Point (P.M.C.C.) >300° F

Specific Gravity 1.05

% Active 100%

% Silicone 18%

Molecular Weight 9,800 (Calculated)

Polyol Type Polyoxyethylene-Polyoxypropylene (EO/PO)

Solubility in Water Soluble (Below 40° C)

Freezing Point - 50° F

APPLICATIONS

Pigment Dispersant

Glass Cleaner Ingredient

Wetting Agent

Shampoo Additive

Thread Lubricant

Polyurethane Foam (Cell Control Agent)

Leveling and Flow Control Agent

Profoaming Additive (Aqueous Systems)



SPECIAL FEATURES

Low Surface Tension

Water Soluble

Low Freeze Point

PROCESSING AND SAFETY GUIDELINES

GP-215 SILICONE POLYOL COPOLYMER has a very low order of toxicity, but should still be handled with all precautions common to the use of any industrial chemical product.

Consult Safety Data Sheet for additional details.

PACKAGING/HANDLING/STORAGE

GP-215 SILICONE POLYOL COPOLYMER is supplied in 5-gallon (40 lbs.) pails, 55-gallon (465 lbs.) drums and 330-gallon (2790 lbs.) totes.

Moisture Sensitive. Keep containers tightly sealed. Store below 100° F.



This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.