

GP-217 SILICONE POLYOL COPOLYMER

Genesee Polymers' *GP-217 SILICONE POLYOL COPOLYMER* is a 100% active polyoxyethylene modified dimethylpolysiloxane block copolymer.

GP-217 is water-soluble and resistant to breakdowns by hydrolysis due to the presence of stable \equiv Si – C \equiv bonds between silicone and polyol block sections.

GP-217 SILICONE POLYOL COPOLYMER is recommended for use as a wetting agent or emulsifier in water-based coatings, inks, polishes and hard surface cleaners. Additionally, *GP-217* may be used as a dispersing agent for the incorporation of clays, pigments and other powders in water.

TYPICAL PROPERTIES	
Appearance (25° C)	Clear, Colorless to Amber Liquid @ 25° C
Weight/Gallon	8.00 lbs.
Viscosity, 77° F	200 cSt
Flash Point (P.M.C.C.)	>300° F
Specific Gravity	1.06
% Active	100%
% Silicone	33%
Molecular Weight	3,800 (Calculated)
Polyol Type	Polyoxyethylene (EO)
Solubility in Water	Soluble (Up to Approximately 57°C)
Freezing Point	65° F

INNOVATIVE POLYMER TECHNOLOGY

APPLICATIONS

Pigment Dispersant

Wetting Agent

Thread Lubricant

Leveling and Flow Control Agent

Profoaming Additive (Aqueous Systems)

SPECIAL FEATURES

Low Surface Tension

Water Dispersible

Non-Hydrolyzable

PROCESSING AND SAFETY GUIDELINES

GP-217 SILICONE POLYOL COPOLYMER has a very low order of toxicity, but should still be handled with all precautions common to the use of any industrial chemical product.

Consult Safety Data Sheet for additional details.

PACKAGING/HANDLING/STORAGE

GP-217 SILICONE POLYOL COPOLYMER is supplied in 5-gallon (40 lbs.) pails, 55-gallon (440 lbs.) drums and 330 gallon (2640 lbs.) totes.

Moisture Sensitive. Keep containers tightly sealed. Store below 100° F.



This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.