



Product Information

GP-226 SILICONE POLYOL COPOLYMER

GeneSee Polymers' *GP-226 SILICONE POLYOL COPOLYMER* is a 100% active polyoxyethylene modified dimethylpolysiloxane block copolymer.

GP-226 is water-dispersible and resistant to breakdown by hydrolysis due to the presence of stable $\equiv \text{Si} - \text{C} \equiv$ bonds between silicone and polyol block sections.

GP-226 SILICONE POLYOL COPOLYMER is recommended for use as a wetting agent or emulsifier in water-based coatings, inks, polishes and hard surface cleaners. Additionally, *GP-226* may be used as a dispersing agent for the incorporation of clays, pigments and other powders in water.

TYPICAL PROPERTIES	
Appearance	Clear, Colorless to Straw Liquid
Weight/Gallon	8.5 lbs.
Viscosity, 77° F	138 cSt
Flash Point (P.M.C.C.)	>300° F
Specific Gravity	1.04
% Active	100%
% Silicone	42%
Molecular Weight	4,340 (Calculated)
Polyol Type	Polyoxyethylene (EO)
Solubility in Water	Dispersible
Freezing Point	32° F

INNOVATIVE POLYMER TECHNOLOGY

APPLICATIONS

Pigment Dispersant

Wetting Agent

Thread Lubricant

Leveling and Flow Control Agent

Profoaming Additive (Aqueous Systems)

SPECIAL FEATURES

Low Surface Tension

Water Dispersible

Non-Hydrolyzable

Low Freeze Point

PROCESSING AND SAFETY GUIDELINES

GP-226 SILICONE POLYOL COPOLYMER has a very low order of toxicity, but should still be handled with all precautions common to the use of any industrial chemical product.

Consult Safety Data Sheet for additional details.

PACKAGING/HANDLING/STORAGE

GP-226 SILICONE POLYOL COPOLYMER is supplied in 5-gallon (40 lbs.) pails, 55-gallon (460 lbs.) drums and 330-gallon (2760 lbs.) totes.

Moisture Sensitive. Keep containers tightly sealed. Store below 100° F.



www.gpcsilicones.com

This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.