




Product Information

GP-369 CYCLOPENTASILOXANE (D5)

Genesee Polymers' *GP-369 CYCLOPENTASILOXANE (D5)* is an intermediate useful for synthesis of silicone fluids. *GP-369* may also be used as a carrier in several cosmetic applications.



TYPICAL PROPERTIES	
Appearance	Clear, Colorless Liquid
Purity	>96.5%
Boiling Point	410° F (210°C)
Flash Point (P.M.C.C.)	163° F (73°C)
Specific Gravity	0.95
Viscosity @ 20° C	3.9 cSt

INNOVATIVE POLYMER TECHNOLOGY

PROCESSING AND SAFETY GUIDELINES

Genesee Polymers' *GP-369 CYCLOPENTASILOXANE (D5)* should be handled with care. Use proper precautions for handling Flammable Materials. Consult Safety Data Sheet for additional details.

PACKAGING/HANDLING/STORAGE

GP-369 CYCLOPENTASILOXANE (D5) is supplied in 5-gallon (38 lbs.) pails and 55-gallon (427 lbs.) drums.

GP-369 is Flammable. Keep away from open flames or welding torches, even when empty. Moisture Sensitive - maintain under nitrogen.



www.gpcsilicones.com

This information is based on tests believed to be reliable. It is given only for your information and no warranty, GPress or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.