



## Product Information

### GP-421 Silicone Resin Emulsion

Genesee Polymers' *GP-421 SILICONE EMULSION* is an emulsion of a reactive, further curable silicone resin in water carrier. *GP-421* may be applied to porous substrates such as wood, leather, textiles or masonry to impart water repellency properties - blocking penetration of liquid water, while still allowing moisture in the vapor phase to pass through.

*GP-421 SILICONE EMULSION* may be used as a component in paints or coatings intended primarily for exterior applications, where the silicone resin component will improve weathering resistance and allow moisture transfer.

Heating substrates treated with *GP-421* will accelerate cure of the resin component of *GP-421*, with the following schedule determined for aluminum substrates:

150° C (302° F) 8 Hours

175° C (347° F) 3 Hours

200° C (392° F) 1 Hour

Cure times at various temperatures will be reduced on substrates such as masonry, because of the alkaline nature of masonry, which helps catalyze the resin curing reaction.

**INNOVATIVE POLYMER TECHNOLOGY**

<b>TYPICAL PROPERTIES</b>	
<b>Appearance</b>	<b>White Opaque Liquid</b>
<b>Weight/Gallon</b>	<b>8.0 lbs.</b>
<b>Flash Point (P.M.C.C.)</b>	<b>204°C</b>
<b>Specific Gravity</b>	<b>1.02 g/ml</b>
<b>Solids Content</b>	<b>42%</b>
<b>Diluent</b>	<b>Water</b>
<b>pH</b>	<b>6</b>
<b>Silicone Resin Content</b>	<b>36%</b>

<b>APPLICATIONS</b>
<p><b>Latex Paint Additive (Improve Weathering)</b></p> <p><b>Water Repellent Formulations</b></p> <p><b>Binder in High Temperature Paints</b></p> <p><b>Protective Coatings</b></p> <p><b>Aqueous Adhesive Formulations</b></p>

<b>SPECIAL FEATURES</b>
<p><b>Stable Emulsion Concentrate</b></p> <p><b>Good Water Repellency</b></p> <p><b>Dilutable with Water</b></p>



## PROCESSING AND SAFETY GUIDELINES

**GP-421 SILICONE EMULSION** should be mixed prior to use to insure homogeneity. Refer to Safety Data Sheet for safety requirements.

## PACKAGING/HANDLING/STORAGE

**GP-421** is supplied in 5-gallon (40 lbs.) pails, 55-gallon (440 lbs.) drums and 330-gallon (2640 lbs.) totes.

Keep container tightly sealed. Do not freeze. Do not store above 100° F.



[www.gpcsilicones.com](http://www.gpcsilicones.com)

This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.