

GP-70-S PAINTABLE SILICONE FLUID

Genesee Polymers' *GP-70-S PAINTABLE SILICONE FLUID* is a 100% active methylalkylaryl silicone designed to provide good release of molded metal, plastic or rubber parts.

GP-70-S is compatible with most organic coatings and adhesives, allowing subsequent coating of molded parts without unusual surface preparation.

| TYPICAL PROPERTIES | |
|------------------------|--|
| Appearance | Clear, Colorless to Light Amber Liquid |
| Weight/Gallon | 7.7 lbs. |
| Viscosity | 1200 cSt |
| Flash Point (P.M.C.C.) | >300° F |
| Specific Gravity | 0.93 |
| % Active | 100% |
| Solubility | Aliphatic Hydrocarbons, Chlorinated Solvents |

Product Code: C-3025 Revised: 02/09/2019

APPLICATIONS

Internal Lubricant/Rubber (Improves Flow, Acts as Internal Mold Release Agent)

Internal Lubricant/Vinyl Plastisols

Rubber Molding (Release Agent)

Paint Additive (Improves Leveling)

Plastic Molding (Release Agent)

SPECIAL FEATURES

Ease of Cleaning

Lubricity

Compatibility with Paints, Coatings and Adhesives

PROCESSING AND SAFETY GUIDELINES

Genesee Polymers' *GP-70-S PAINTABLE SILICONE FLUID* has been formulated to give good compatibility with organic coatings and adhesives. Nonetheless, surfaces contaminated with *GP-70-S* should be cleaned properly before painting or bonding - as is true even with conventional petroleum oil contaminants. For safety requirements, refer to Safety Data Sheet.

PACKAGING/HANDLING/STORAGE

GP-70-S PAINTABLE SILICONE FLUID is supplied in 5-gallon (35 lbs.) pails, 55-gallon (400 lbs.) drums and 330-gallon (2400 lbs.) totes.

GP-70-S should be handled with the same precautions common to the use of industrial products.



www.gpcsilicones.com

This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.