

TYPICAL PROPERTIES	
Appearance	Clear, Light Straw Liquid
Viscosity	750 cSt
Flash Point (P.M.C.C.)	>200° F
Weight/Gallon	8.0 lbs.
Molecular Weight	7,800 (Theory)
Specific Gravity	1.0
Solubility	Aliphatic Hydrocarbons, Chlorinated Solvents

APPLICATIONS
<p>Internal Lubricant in Rubber</p> <p>Molding Hoses on Mandrels</p> <p>Internal Release Agent in Rubber, Plastics and Plasticsols</p> <p>Intermediate in Silicone - Organic Copolymer Synthesis</p> <p>Foundry Release Agents</p>

SPECIAL FEATURES
<p>Ease of Cleaning</p> <p>Amine Alkyl Functional</p> <p>Superior Release Performance in Plastic and Rubber Molding</p> <p>Good Lubricant for Metal Cutting and Drilling, Particularly Aluminum</p>



PROCESSING AND SAFETY GUIDELINES

Genesee Polymers' *GP-7100 SILICONE FLUID* has been formulated to provide good compatibility with organic coatings and adhesives. Nonetheless, surfaces contaminated with *GP-7100* should be cleaned properly, before painting or bonding - as is true even with conventional petroleum oil contaminants.

GP-7100 SILICONE FLUID should be handled with the same precautions common to the use of industrial products. May cause eye and skin irritation. For additional precautions, refer to Safety Data Sheet.

PACKAGING/HANDLING/STORAGE

GP-7100 SILICONE FLUID is supplied in 5-gallon (40 lbs.) pails, 55-gallon (440 lbs.) drums and 330-gallon (2640 lbs.) totes.



www.gpcsilicones.com

This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.