



Product Information

GP-846 AMINE FUNCTIONAL SILICONE FLUID

Genesee Polymers' *GP-846* is an Amine Functional Silicone Fluid that contains both amine alkyl and hydrolyzable alkoxy groups.

The combination of amine and alkoxy groups suggests primary applications in mold-release agents and detergent resistant polishes.

GP-846 AMINE FUNCTIONAL SILICONE FLUID is 100% active and can also be used in water repellent formulations or in organic - silicone copolymer synthesis.

TYPICAL PROPERTIES	
Appearance	Clear to Slightly Hazy, Straw to Colorless Liquid
Weight/Gallon	8.0 lbs.
Viscosity	55 cSt
Flash Point (P.M.C.C.)	>300° F
Specific Gravity	0.98
Equivalent Weight	1,440 gms. per Amine Group
% Active	100%
Base Equivalent *	0.693

* Milliequivalents of base per gram of fluid

INNOVATIVE POLYMER TECHNOLOGY

APPLICATIONS
<p>Car Polishes</p> <p>Vinyl Conditioners</p> <p>Water Repellents</p> <p>Rust Inhibitor Additive</p> <p>Leather Treatment</p> <p>Textile Lubricants</p> <p>Organic - Silicone Copolymer Synthesis</p>

PROCESSING AND SAFETY GUIDELINES

GP-846 AMINE FUNCTIONAL SILICONE FLUID may be blended with solvents, waxes or high viscosity silicone fluids for car polish or vinyl conditioners. **GP-846** can also be formulated into emulsions.

The physiological and toxicological properties of **GP-846 AMINE FUNCTIONAL SILICONE FLUID** are similar to those of other amine functional silicone fluids currently on the market. Precautions should be the same as required for handling long chain organic alkyl amines. Avoid contact with skin and eyes. For additional safety precautions, refer to the Safety Data Sheet.

PACKAGING/HANDLING/STORAGE

GP-846 AMINE FUNCTIONAL SILICONE FLUID is supplied in 5-gallon (40 lbs.) pails, 55-gallon (440 lbs.) drums and 330-gallon (2640 lbs.) totes.

Moisture Sensitive. Keep containers tightly sealed when not in use.



www.gpcsilicones.com

This information is based on tests believed to be reliable. It is given only for your information and no warranty, express or implied, is made as we cannot guarantee the test conditions not under our direct control. This data is not intended as authorization or recommendation to practice a patented invention without knowledge or permission of the patent owner.